



JK MAJESTA TRU-PEARL

Luxury Interior Emulsion

MAJESTA TRU-PEARL is a Luxury Interior Emulsion that offers a high-quality, pearl-like lustrous finish, extending exquisiteness to painted interior spaces. Its unique formulation gives unmatched smoothness to surfaces like walls, ceilings and the like.

PRODUCT BENEFITS/FEATURES



Teflon Like Strength



4D Finish



Rich Sheen



Stain Resistant



Low-VOC



Interior



ChromaSure® Tech

AREAS OF APPLICATION

JK Majesta Tru-pearl Luxury Interior Emulsion can be applied on cement plaster, concrete bricks, asbestos, RCC works, wood & board, and cement sand renderings.

PACKAGING AVAILABLE



1 L



4 L



10 L



20 L

COVERAGE

On normal masonry surface by brush/roller/spray



2 Coats 130-150 sq.ft/ltr*

*Actual Coverage may vary from the quoted coverage due to factors such as method and condition of application, surface roughness and porosity.

FINISH

Smooth

Rich Sheen

COLORS AVAILABLE

1000+ Shades

Currently Available as per the JK MaxX Paints Shade Card & Fandek



HOW TO APPLY

SURFACE PREPARATION

- For best results, proper surface preparation is essential. Newly plastered surface should be allowed to mature for 6-8 weeks.
- Surfaces to be painted should be sound, clean, dry and free from dust, dirt, loose particles, grease, chalking, etc., before application of Majesta Tru-pearl.
- This should be done by washing the surface with water.
- All surfaces to be painted should be thoroughly sanded with emery paper 180 and wiped clean.
- All surface seepage or leakage should be properly repaired.
- All fungus/algae-affected areas must be treated.
- Apply a coat of Primera Interior Wall Primer and allow it to dry for 4–6 hours.
- For any surface undulations, apply a thin coat of JKCement WallMaxX Wall Putty and allow it to dry for 4-6 hours.
- Sand the surface with emery paper 180 and wipe it clean.
- Apply another coat of Primera Interior Wall Primer and allow it to dry for 4-6 hours.
- Sand the surface with emery paper 320 and wipe it clean.

APPLICATION

- Apply 2-3 coats by diluting 1 litre of Majesta Tru-pearl with 400–500 ml of water, with an interval of 4-6 hours between the successive coats.
- Majesta Tru-pearl can be applied by brush, roller, or spray.

SAFETY PRECAUTIONS

- Stir the contents thoroughly and strain before use.
- Store Majesta Tru-pearl in a cool and dry place.
- Keep the container tightly closed when not in use.
- Wash the brush/equipment with water immediately after use.

SHELF LIFE

- 3 years from the date of manufacturing in the original tightly closed container, away from direct sunlight and excess heat.
- Lead contents does not exceed 90 ppm.
- No Added Mercury, Arsenic and Chromium.
- Stir well and strain before use.

JK MAJESTA TRU-PEARL APPLICATION PROCESS

APPLICATION	THINNER	DILUTION % VOLUME	APPLICATION VISCOSITY ¹ (SEC)	RECOATING PERIOD ² (HOURS)
Surface Preparation	Cleaning & Sanding with Emery Paper 180			
Step 1 Primera Interior Wall Primer	Water	100%	Brush/Roller 20-25 Spray 20-25	4-6 hours
Step 2 JKCement WallMaxX Wall Putty	Water	Based on requirement	N/A	4-6 hours
	Cleaning & Sanding with Emery Paper 180			
Step 3 Primera Interior Wall Primer	Water	100%	Brush/Roller 20-25 Spray 20-25	4-6 hours
	Cleaning & Sanding with Emery Paper 320			
Step 4 First Coat JK Majesta Tru-pearl Luxury Interior Emulsion	Water	40%-50%	Brush/Roller 30-35 Spray 20-25	4-6 hours
Step 5 Second Coat JK Majesta Tru-pearl Luxury Interior Emulsion	Water	40%-50%	Brush/Roller 30-35 Spray 20-25	4-6 hours

1. As measured through a Ford cup.

2. Recoating period is quoted for 25°C and 50% Relative Humidity, these may vary under different conditions.

3. Some shades may require 3 or more coats for proper hiding.

PRECAUTIONS

- Do not apply when ambient temperature is less than 10°C or if the temperature is expected to drop to this level within 4 hours of application.
- In high humidity areas, remove surface fungus growth, fungal spores, mould etc., before application.
- Tinted paints need thorough shaking / mixing immediately after tinter addition as well as before use.
- Do not thin the paint before addition of Universal Stainer for customized shades.

TECHNICAL DETAILS

Drying time: Surface dry time 30 min.

Sheen levels: 8-12 at 60° GH

Flash point IS101/1987 Part 1, Sec 6: NA

Stability of thinned paint: To be used within 24 hours

SAFETY FEATURES

- Kindly refer to the MSDS for JK Majesta Tru-pearl Luxury
 - Interior Emulsion which gives detailed information on safety measures while handling the paint.
 - Do not breathe vapour or spray. It is recommended to wear suitable nose pad during sanding and surface preparation to avoid dust inhalation.
 - Do not pour leftover paint down the drain or in water courses.
 - In the event of spills, contain spillage using sand or earth.
 - Safety Data Sheet available for professional user on request.
- No added Lead, Mercury or Chromium compounds.
 - Store the container with the lid tightly closed in an upright position, in a cool, dry place.
 - Keep out of reach of children and away from food, drink etc.
 - Maybe harmful, if swallowed. In case of ingestion, seek immediate medical attention.
 - Wear eye protection during application. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.
 - In case of skin contact immediately wash skin with soap and plenty of water. Get medical attention if irritation develops or persists.