


SURFACE PREPARATION

The surface should be dry clean and free dirt grease algal and fungal growth. New plastered surface should be allowed to cure for at least 28 days. Surface imperfection should be removed with the use of JK WallMaxx Putty as per directions.



THINNING

- a) Can be thinned COLORATO BASE with 2-3 % potable water as per requirement.
- b) No thinner required for application of COLORATO TOP



PACKING

Available in 20 Ltr & 1 Ltr container packing.



PRECAUTION



Avoid application in temperatures over 40°C and below 5°C and in strong winds. Wash all application equipment with water immediately after use.

FINISH

High build smooth, multicolor, acrylic, textured finish by Spray Gun.



JK MAJESTA Artiste VOGUE

Colorato



JK Cement Ltd.

Kamla Tower, Kanpur, UP - 208001
Toll-free Number: 1800 203 4555 | Website: www.jkmaxxpaints.com
Email Address: consumercare@jkmaxxpaints.com



JK MAJESTA
Artiste VOGUE

Colorato
MULTICOLOR DESIGN FINISH

COLORATO provides beautiful decorative effects reminiscent of colours used inside mansions. Widely liked by interior decorators available in metallic and non metallic shades .



TECHNICAL DATA

PRODUCT BENEFITS/FEATURES



Smooth multicolor finish



Excellent weather and natural colour resistance



Good flexibility and adhesion



Algae & Fungus resistance



Breathes out trapped moisture



Water Repellent

APPLICATION AREA

Exterior and interior of cement sand plasters, Stucco, Concrete, Gypsum Boards, Bricks, wood. etc.




COMPOSITION

It is based on high performance Acrylic Resin with silicone, Quartz, Siliceous Minerals, Special Biocides, Fungicides, Algacides and Surfactants etc. It is also recommended for reviving old buildings.



COVERING CAPACITY

Approx. 4.5- -5.5 sq. ft. per kg. depending on the porosity of the surface.



DRYING TIME

Hard Dry : 12 hours.



APPLICATION

- JK Primera coat as Sealer / Primer of required shade
- Apply the COLORATO base by Trowel as smooth plaster.
- After 24 hrs drying spray the COLORATO TOP as bubbles by spray gun and smoothen this by trowel.
- After 12 hrs drying apply one coat of TC 100 A (Acrylic Dirt Resistant Top Coat) over the surface by brush /roller.

